

### Print carrier

### Average values

**JAC® Radial** is a series of papers in fluorescent colours, coated on one side. They are distinguished by their extremely high daylight fluorescence and are intended for the production of eye-catching labels and stickers, e.g. warning notices, advertising stickers etc.

**Radial Orange FSC® Certified** – The face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

**Radial Yellow FSC® Certified** – The face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

**Radial Green FSC® Certified** – The face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

**Radial Red FSC® Certified** – The face material, FSC® C011032 certified, is sold as FSC® Mix Credit.

For technical guidance please visit our website under downloads "Guidelines for use – Offset printing."

	Radial Orange FSC® Certified	Radial Yellow FSC® Certified	Radial Green FSC® Certified	Radial Red FSC® Certified
Weight (g/m <sup>2</sup> )	78	78	78	78
Thickness (µm)	73	73	73	73
Tensile strength longitudinal (kN/m)	5-7.6	5-7.6	5-7.6	5-7.6
Opacity (%)	89	89	89	89
Shelf life of laminate <sup>1)</sup> (years)	2	2	2	2

<sup>1)</sup> Refers to adhesion and printability when stored in original packaging in dark, dry conditions at a temperature of 22 ± 2°C and a relative humidity of 50% ± 5%.

For information regarding EHS regulation, please visit our website under downloads "Guidelines for Use 5.12 Product Compliance JAC Offset".

### Adhesive

### Average values

**DURO D 2000** is a dispersion-based permanent acrylic adhesive displaying very good processing properties and excellent guillotining behaviour. Its good adhesion permits use on a diversity of surfaces, such as paper, steel, glass etc. It also displays very good UV stability.

	DURO D2000
Adhesion (N/25 mm) (FTM2 on st. steel/20 min. bond time)	9.2
Tack (N/25 mm) (FTM9 on glass)	9.6
Recommended minimum application temperature (°C)	>+5
Heat resistance up to 24 hrs (°C)	+80
up to 1 hr (°C)	+110
Resistance to cold (°C) <sup>2)</sup> down to	- 40

<sup>2)</sup> Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

### Silicone paper

### Average values

**B 85** – a siliconized, wood-free, special-purpose paper. It is moisture-stabilized through a special coating on one side. B85 displays high dimensional stability and excellent flatness. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

**B 110** – a siliconized, wood-free, special-purpose paper. It is moisture-stabilized and displays very high dimensional stability and excellent flatness. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

	B 85	B 110
Weight (g/m <sup>2</sup> )	78	86
Thickness	82	87

Issue May 2021

#### Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

JAC® is registered trademark of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.