

Properties	Test method	Unit	IEASY® Foam Print SF
Mechanical properties			
Density	MSZ ISO 1183	g/cm ³	0,5
Tensile strength	MSZ EN ISO 527- 1.2	M P a	>12
Elongation at reak	MSZ EN ISO 527- 1.2	%	~15
Modulus of elasticity	MSZ EN ISO 527- 1.2	M P a	>750
Impact strength	MSZ EN ISO 179-2	kJ/m ²	12
Shore D	MS EN ISO 868	-	>40
Thermal properties			
Vicat B	MSZ EN ISO 306	°C	72
		°F	162
Linear thermal expansion	DIN 53752	K ⁻¹ x10 ⁻⁴	0,75
Thermal conductivity	DIN 52612	W/mK	0,08
Electronical properties			
Dielectric strength	MSZ EN 60243-1	kV/mm	13
Surface resistivity	DIN 53482	Ohm	>5x10 ¹⁴
General properties			
Fire rating	DIN 4102 (D)	-	B1 (3mm)
	BS 476-7 (GB)	-	Class 1 (2 – 10mm)
	CSE RF 3/77 (I)	-	Class 1 (2 – 10mm)
	NFP 92-501 (F)	-	M1 (2 – 10mm)
	UL 94 (US)	-	V0
Water absorption	DIN 53495	%	<1
Working temperatue range	-	°C	0-60
		°F	32-140

