

Oppboga Excellent Card

Multi-layer solid bleached board, double coated on both sides

THICKNESS		SUB-STANCE	BENDING RESISTANCE L&W 15° mN		BENDING MOMENT Taber 15° mNm	
pt	mm		MD	CD	MD	CD
20	0.50	450	790	390	38	19
28	0.72	600	1950	1000	94	48
40	1.00	860				



White. Smooth. Vibrant.

APPLICATIONS

Gift cards • signs • point of sale displays

PRINTING

Offset printing • screen printing • large format digital printing

CONVERSION

Embossing • foil and film lamination • varnishing • die cutting • creasing • perforating • cutting and scoring

ADDITIONAL INFORMATION

www.oppboga.com

Tolerances / Testing Standards

Grammage (DIN ISO 536)±6%
Thickness (DIN ISO 534)±6%
Bending stiffness (ISO 5629)-15%
ISO Brightness C/2° (ISO 2470) min. 92
Smoothness (ISO 8791-4) max 1.4µm

Printing Surface Properties

ISO Brightness95
CIE Whiteness D65/10° (ISO 11475) 135
Surface smoothness (PPS) 0.9µm
Gloss 75° (ISO 8254-1) 48%